



TECHNICAL DATA

DU22500 FIRE RETARDANT WHITE

4.0 MIL

20" X 500' WHITE POLY DUCT WITH AIRJETS

<u>FILM PROPERTIES</u>	<u>ASTM METHOD</u>	<u>UNITS</u>	<u>TYPICAL VALUE</u>
MELT INDEX	D-1238	g/10 MIN.	1.3
DENSITY	D-1505	g/cm	0.96
WHITE	LOADING	%	AS SELECTED
GLOSS	D-2457	%	40
TENSILE STRENGTH	D-882	PSI	
MD			3200
TD			2650
ULTIMATE ELONGATION	D-882	%	
MD			450
TD			800
SECANT MODULUS (1%)	D-882	PSI	
MD			27000
TD			31000
YIELD @ 4.0MIL		SQ. IN /LB	